

## TP 430 • 1.4016

Stainless steel type 1.4016 is also commonly known as grade 430. Type 430 stainless steel combines good corrosion resistance with good formability and ductility. It is a ferritic, non-hardenable plain Chromium stainless steel with excellent finish quality. Grade 430 also has excellent resistance to nitric attack, which makes it well suited to use in chemical applications.

Material grade	Norm	Chemical composition • mass in %									
		C	Si	Mn	P	S	Cr	Ni	Mo	Ti	Sonst.
		max.	max.	max.	max.	max.	min. – max.	min. – max.	min. – max.		
1.4016	EN 10297-2	0,080	1,00	1,00	0,040	0,030	16,00 - 18,0 0	0,75	-	-	-
TP430	ASME SA / AS TM A 268	0,120	1,00	1,00	0,040	0,030	16,00 - 18,0 0	-	-	-	-

Material grade	Norm	Mechanical properties and heat treatment					
		Rp 0,2 [MPa]	Rp 1,0 [MPa]	Rm [MPa]	A [%]	Härte	Wärmebehandlung
		min.	min.	min. – max.	min	HRB max.	
1.4016	EN 10297-2	240	250	430	20	-	geglüht
TP430	ASME SA / AS TM A 268	240	-	415	20	95	geglüht

Tolerances				
AD - Rohr	AD	WD	special WT	ID
ab Ø4,550 mm	±0,050 mm	±0,150 mm	±0,100 mm	X
ab Ø9,530 mm	±0,050 mm	±0,100 mm	±0,080 mm	±0,050 mm
ab Ø30,001 mm***	±0,100 mm	±0,150 mm		±0,050 mm

\*\*\* to max. ø44,500 mm

- Tolerances acc. to DIN EN 10305-1 can be confirmed to OD 30mm
- Tolerances acc. to DIN EN ISO 1127 / DIN EN 10216-5 can be confirmed
- Tolerances acc. to ASTM can be confirmed generally

Abmessungsbereich\*

Abmessungsspektrum

AD	WD	[mm]	0,89	1,00	1,20	1,24	1,65	1,82	2,00	2,11	2,30	2,35	2,50	2,60	2,64	2,77	2,87	3,00	3,20	3,25	3,60	3,85	3,91	4,00	4,40	5,50	6,35	7,00
[mm]	[inch]	[inch]	0,035			0,048	0,065	0,072		0,083		0,093			0,104	0,109	0,113		0,126	0,128			0,154				0,250	
6,00																												
6,35	0,250																											
7,00																												
7,50																												
8,00																												
9,00																												
9,53	0,375																											
10,00																												
11,00																												
12,70	0,500																											
13,00																												
15,00																												
15,88	0,625																											
16,00																												
16,80																												
17,15	0,675																											
18,00																												
19,00																												
19,05	0,750																											
20,00																												
21,34	0,840																											
22,00																												
22,23	0,875																											
23,00																												
25,00																												
25,40	1,000																											
26,00																												
26,67	1,050																											
28,00																												
30,00																												
31,75	1,250																											
32,00																												
33,40	1,315																											
36,00																												
38,10	1,500																											
42,00																												
44,50	1,750																											

