

N08020 • 2.4660 • TPS-Techalloy 20

ALLOY 20 is a nickel-iron-chromium alloy with addition of copper and Molybdenum. Stabilized with niobium against sensitization and resultant intergranular corrosion. ALLOY 20 has excellent resistance to general corrosion, pitting and crevice corrosion in chemicals containing chlorides and sulfuric, phosphoric and nitric acids.

Material grade	Norm	Chemical composition • mass in %									
		C	Si	Mn	P	S	Cr	Ni	Mo	Ti	Sonst.
		max.	max.	max.	max.	max.	min. – max.	min. – max.	min. – max.		
2.4660	DIN 17744 / 1 7751	0,070	1,00	2,00	0,025	0,015	19,00 - 21,00	32,00 - 38,00	2,00 - 3,00	Co. 1,50	Cu 3-4; Nb+Ta 8xC max.; Fe Rest
N08020	ASME SB / AS TM B 729	0,070	1,00	2,00	0,045	0,035	19,00 - 21,00	32,00 - 38,00	2,00 - 3,00	-	Cu 3-4; Nb+Ta 8xC max.; Fe Rest

Material grade	Norm	Mechanical properties and heat treatment					
		Rp 0,2 [MPa]	Rp 1,0 [MPa]	Rm [MPa]	A [%]	Härte	Wärmebehandlung
		min.	min.	min. – max.	min	HRB max.	
2.4660	DIN 17744 / 1 7751	240	-	550	40	95	weichgeglüht
N08020	ASME SB / AS TM B 729	240	-	550	30	-	geglüht

Tolerances				
AD - Rohr	AD	WD	special WT	ID
ab Ø4,550 mm	±0,050 mm	±0,150 mm	±0,100 mm	X
ab Ø9,530 mm	±0,050 mm	±0,100 mm	±0,080 mm	±0,050 mm
ab Ø30,001 mm***	±0,100 mm	±0,150 mm		±0,050 mm

*** to max. Ø44,500 mm

- Tolerances acc. to DIN EN 10305-1 can be confirmed to OD 30mm
- Tolerances acc. to DIN EN ISO 1127 / DIN EN 10216-5 can be confirmed
- Tolerances acc. to ASTM can be confirmed generally

Abmessungsbereich*

Abmessungsspektrum

AD	WD	[mm]	0,89	1,00	1,20	1,24	1,65	1,82	2,00	2,11	2,30	2,35	2,50	2,60	2,64	2,77	2,87	3,00	3,20	3,25	3,60	3,85	3,91	4,00	4,40	5,50	6,35	7,00
[mm]	[inch]	[inch]	0,035			0,048	0,065	0,072		0,083		0,093			0,104	0,109	0,113		0,126	0,128			0,154				0,250	
6,00																												
6,35	0,250																											
7,00																												
7,50																												
8,00																												
9,00																												
9,53	0,375																											
10,00																												
11,00																												
12,70	0,500																											
13,00																												
15,00																												
15,88	0,625																											
16,00																												
16,80																												
17,15	0,675																											
18,00																												
19,00																												
19,05	0,750																											
20,00																												
21,34	0,840																											
22,00																												
22,23	0,875																											
23,00																												
25,00																												
25,40	1,000																											
26,00																												
26,67	1,050																											
28,00																												
30,00																												
31,75	1,250																											
32,00																												
33,40	1,315																											
36,00																												
38,10	1,500																											
42,00																												
44,50	1,750																											

